

## Terra Bella™ Resin Chart by Color

Color Name/Code	Resin Percent by Weight Using a 1,000 cps Swing Resin (others differ)	Sample Mix Example
Monte Bianco GTB 300	20% resin on average.	500 grams GTB 300 130 grams resin @1000 cps 2.6 g catalyst
El Tigre GTB 301	18% resin on average.	500 grams GTB 304 112 grams resin @1000 cps 2.24 grams catalyst
Pompeii GTB 302 <i>*2.25 to 2.5% catalyst recommended</i>	20% resin on average.	500 grams GTB 302 130 grams resin 2.6 g catalyst
Citrine Crema GTB 303	20% resin on average.	500 grams GTB 303 130 grams resin 2.6 g catalyst
Rosa GTB 304	18% resin on average.	500 grams GTB 304 112 grams resin 2.24 grams catalyst
Amethyst Regio GTBE 305	20% resin on average.	500 grams GTB 305 130 grams resin 2.93 grams catalyst
Antigua Blue GTB 306	20% resin on average.	500 grams GTB 306 130 grams resin 2.6 g catalyst
Hematite Gold GTB 307 <i>*This color contains over 6% pyrite, which retards the cure time. More catalyst might be desired.</i>	20% resin on average.	500 grams GTB 307 130 grams resin 2.93 g catalyst <i>*2.25% catalyst suggested</i>
Blue Mosaic GTB 308 <i>*This color contains over 5% pyrite, which retards the cure time. More catalyst might be desired.</i>	22% resin on average.	500 grams GTB 308 140 grams resin 3.15 g catalyst
Verde Mosaic GTB 309 <i>*This color contains over 5% pyrite, which retards the cure time. More catalyst might be desired.</i>	22% resin on average.	500 grams GTB 309 140 grams resin 3.15 g catalyst
Turquoise Montagna GTBE 310	20% resin on average.	500 grams GTB 310 130 grams resin 2.6 g catalyst
Roma GTB 311	20% resin on average.	500 grams GTB 311 130 grams resin 2.6 grams catalyst
Paprika GTB 312 <i>*This color may have a retarded gel time and need more catalyst.</i>	20% resin on average.	500 grams GTB 312 130 grams resin 2.26 grams catalyst
Vittoria GTB 313	20% resin on average.	500 grams GTB 313 130 grams resin 2.6 g catalyst
Crystal Colors GTBE and GTB colors 315–320	20% resin on average.	500 grams GTB 308 130 grams resin 2.6 g catalyst